

Product Data Sheet

70714/70715 – 2K Epoxy

45060: Base 45069 : Curing Agent 95073



Description: 70714/70715 (Hempel 45069/95073) is a two-component, 100% solids epoxy resin.

Recommended use: Applications include: High-gloss, high-build protective coating; binder for self-smoothing pigmented and color quartz flooring; low-viscosity binder for trowel-applied mortar flooring systems; high-quality primer for chemical resistant urethane top coats, and/or NEOGARD® waterproofing and flooring systems; low-viscosity binder for trowel applied mortar and/or patching material; low viscosity binder for crack injection.

Features: Formulated for use on damp or dry concrete. Near water-clear. Exhibits no amine blush when used in humid environments. Very low viscosity for deep penetration into concrete. Uniform wetting of filler aggregates. Excellent chemical and water resistance. Meets U.S.D.A. requirements for incidental food contact. Meets South Coast Air Quality Management District (SCAQMD) VOC requirements.

Certificates/approvals: LEED: MRc5, IEQc4.2
MPI: MPI #212

Availability: Available in North America. Not included in Group Assortment; other regions must confirm.

Colors and packaging:

70714 (4506900000)	Clear	15- and 3-gallon kits
70714-01 (4506916640)	White	15- and 3-gallon kits
70714-02 (4506916650)	Gray	15- and 3-gallon kits
70714-03 (4506923820)	Tan	15- and 3-gallon kits
70714-04 (4506916670)	Dark Gray	15- and 3-gallon kits
70714-05 (4506957930)	Tile Red	15- and 3-gallon kits
70714-11 (4506916660)	Light Gray	15- and 3-gallon kits
70714-16 (4506919990)	Black	15- and 3-gallon kits
70714-06 (4506949890)	Green	3-gallon kits
70715 (9507300000)	NA	Curing agent, included in kits

Some standard colors and/or packaging may have extended lead times and/or minimum quantities. Contact NEOGARD® for additional colors.

Physical constants:

Tensile Strength	3,700 psi	ASTM D638
Elongation	25%	ASTM D638
Compressive Strength	25,300 psi	ASTM D695
Flexural Strength	3,180 psi	ASTM D790
Flexural Modulus	57,700 psi	ASTM D790
Water Resistance	0.21%	ASTM D570
MVT @ 10 Mills	0.16	ASTM E96
Taber Abrasion	25 mg/1,000 CS-17	ASTM D4060
Shore D	78	ASTM D2240
Adhesion	350 psi	ASTM D4541
Flammability	Pass	ASTM D635
Weight/Gallon (mixed)	8.8 lbs/gal	ASTM D1475
Weight Solids (mixed)	100%	ASTM D4209
Volume Solids (mixed)	100%	Calculated
VOC (mixed)	<10 g/L	EPA Method 24
Flash Point	>200°F (93°C)	ASTM D3278
Shelf Life	1 year	
Thin Film Cure @ 75°F (23°C)	8–9 hours	
Full Cure @ 75°F (23°C)	7 days	
Full Chemical Resistance	7 days	

The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at www.neogard.com.

Product Data Sheet

70714/70715 – 2K Epoxy

45060: Base 45069 : Curing Agent 95073



Application details:

Version, mixed product	45060
Mixing ratio:	Base 45069 : Curing Agent 95073 2 : 1 by volume
Mixing instructions:	Pre-mix base for 3–5 minutes before adding curing agent. Mix for a minimum of 5 minutes before applying. Jiffy Mixer paddle recommended.
Application method:	Roller or squeegee
Thinner (max.vol.):	7055 Odorless Reducer (086JB) or HEMPEL'S THINNER 08080 (xylene) (10%)
Pot life:	30 minutes at 70°F (21°C)
Cleaning of tools:	7055 Odorless Reducer (086JB) or HEMPEL'S THINNER 08080 (xylene)
Safety:	Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult NEOGARD® Safety Data Sheets and follow all local or national safety regulations.
Surface preparation:	According to NEOGARD® Guide Specifications.
Application conditions:	Ambient temperature must be between 40°F (4°C) and 100°F (37°C), and a minimum of 5°F (3°C) above dew point.
Preceding coat:	According to NEOGARD® Guide Specifications.
Subsequent coat:	According to NEOGARD® Guide Specifications.
Storage temperature:	Store in a cool area to ensure full shelf life. Recommended temperature: 70°F (21°C).

Note: **70714/70715 (45060) is for professional use only.**

Issued by: Hempel A/S – 45060

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 70714-70715-PDS ksk 05042018.docx

NEOGARD®, a Division of Hempel (USA), Inc.
2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com