

# Product Data Sheet

70800/70801/70804 — Neocrete SL

48010: Base 48019 : Curing Agent 98010 : Aggregate 66022



**Description:** Neocrete SL (70800/70801/70804, Hempel 49019/98010/66022) is a self-leveling, water-dispersed polyurethane resin combined with a powder aggregate.

**Recommended use:** As a surfacing/resurfacing system applied to the following substrates: concrete, polymer reinforced screeds, and properly supported wood floors.

**Features:** High abrasion, impact, and chemical resistance. Resistant to thermal shock stresses such as hot water and daily steam cleaning. Resistant to acids, caustics, fuels, oils, and solvents. Steel troweled in one step; requires no primers or sealers. Meets U.S.D.A. requirements for incidental food contact. Meets South Coast Air Quality Management District (SCAQMD) VOC requirements.

**Service temperatures:** -120°F (-84°C) – 210°F (99°C)

**Certificates/approvals:** LEED: MRc5, IEQc4.2

**Availability:** Available in North America. Not included in Group Assortment; other regions must confirm.

## Colors and packaging:

70800-02 (4801916650)	Gray	2-gallon can, 156 fluid oz. fill
70800-05 (4801957930)	Red	2-gallon can, 156 fluid oz. fill
70800-031 (4801923820)	Desert	2-gallon can, 156 fluid oz. fill
70801 (9801000000)	NA	1-gallon can, 126 fluid oz. fill
70804 (6602209990)	NA	53-lb bag

*Some standard colors may have extended lead times and/or minimum quantities.*

## Physical constants:

Compressive Strength	7,700 psi	ASTM C579
Tensile Strength	712 psi	ASTM C307
Flexural Strength	2,200 psi	ASTM C580
Modulus of Elasticity	446,700 psi	ASTM C580
Shore D	84	ASTM D2240
Adhesion (concrete)	400 psi	ASTM D4541
Water Resistance	0.42%	ASTM C413
Density	121 lbs/ft <sup>3</sup>	ASTM C905-01
Coefficient of Thermal Expansion	2.4 x 10 <sup>-5</sup> in/in/°F	ASTM C531
Resistance to Fungal Growth	No Support of Growth	ASTM G21
Flammability	Pass	ASTM D635
Weight Solids (mixed)	99.95%	ASTM D5201
Volume Solids (mixed)	99.93%	ASTM D5201
Flash Point	None	ASTM D3278
VOC (mixed)	8.4 g/L	ASTM D5201
Shelf Life	1 year	
Typical Thickness	3/16"	
Mixed Unit Coverage @ 3/16"	38–40 square feet	
Initial Join Up Time @ 70°F (21°C) per 1/4"	20 minutes	
Cure to Foot Traffic @ 70°F (21°C) per 1/4"	4–8 hours	
Cure to Full Use @ 70°F (21°C) per 1/4"	10–16 hours	

*The above tested results are typical values. Individual lots may vary up to 10% from the typical value. Further technical information can be found at [www.neogard.com](http://www.neogard.com).*

# Product Data Sheet

70800/70801/70804 — Neocrete SL

48010: Base 48019 : Curing Agent 98010 : Aggregate 66022



## Application details:

### Version, mixed product

Mixing ratio:

### Neocrete SL 48010

Base 48019 : Curing Agent 98010 : Aggregate 66022

Mix 200 fluid ounces of 70800 (one 2-gallon can) with 126 fluid ounces of 70801 (one 1-gallon can) and one 53-pound bag of 70804 powder. Mix with a variable speed drill utilizing a Jiffy Mixer to suspend any settled pigment and attain a uniform color. Time will vary depending on temperature conditions.

IMPORTANT: Pre-mix 70800 for a minimum of one minute before mixing with 70801 hardener. To avoid color variation from mix to mix, scrape all of the pre-mixed 70800 from the 70800 can into the mixing container.

Application method:

Steel trowel, screed box, gauge rake

Thinner (max.vol.):

Contact NEOGARD® for thinning instructions

Pot life:

15 minutes at 70°F (21°C)

Cleaning of tools:

7055 Odorless Reducer (086JB) or HEMPEL'S THINNER 08080 (xylene)

### Safety:

Handle with care. Use with adequate ventilation. Before and during use, observe all safety labels on packaging and paint containers, consult NEOGARD® Safety Data Sheets and follow all local or national safety regulations.

### Surface preparation:

According to NEOGARD® Guide Specifications.

### Application conditions:

Ambient temperature must be between 50°F (10°C) and 85°F (29°C), and a minimum of 5°F (3°C) above dew point.

### Preceding coat:

According to NEOGARD® Guide Specifications.

### Subsequent coat:

According to NEOGARD® Guide Specifications.

### Storage temperature:

Store in a cool area to ensure full shelf life. Recommended temperature: 70°F (21°C).

### Remarks:

For maximum adhesion, correct surface preparation is essential. Regular cleaning of applied surface is recommended in order to maintain slip resistance and aesthetics.

Note:

**70800/70801/70804 — Neocrete SL (48010) is for professional use only.**

Issued by:

Hempel A/S – 48010

This Product Data Sheet supersedes those previously issued.

Manufacturer warrants that the physical properties of the product reported above will meet the standards and deviations of the associated ASTM test method. MANUFACTURER HEREBY EXPRESSLY DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY IMPLIED WARRANTY OF MERCHANTABILITY AND/OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE. Buyer must make its own determination of the suitability of any product for its use, whether such product is used alone or in combination with other materials. To the extent this or any of Manufacturer's products is proven to be defective, Buyer's sole remedy shall be limited to the replacement of such defective product, exclusive of any costs of labor. MANUFACTURER SHALL NOT BE LIABLE OR OBLIGATED FOR ANY LOSS OR CONSEQUENTIAL OR OTHER DAMAGE INCURRED DIRECTLY OR INDIRECTLY BY BUYER OR ANY OTHER PERSON OR ENTITY THAT ARISES IN ANY WAY IN RELATION TO THIS OR ANY OF MANUFACTURER'S OTHER PRODUCTS. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority of the owner of the patent. No Applicator is or should be viewed as an employee or agent of Manufacturer. 70800-70801-70804-PDS ksk 08222018.docx

NEOGARD®, a Division of Hempel (USA), Inc.

2728 Empire Central - Dallas, Texas 75235 - Phone (214) 353-1600 - Fax (214) 357-7532 - www.neogard.com